

Number	17-003553-PR01 (NW-K15-09-en-01)
Owner	Kiilto Oy P.O. Box 250 33101 Tampere Finland
Product	Wood adhesive
Designation	System: PVAc dispersion Shipping name: Kestokol D 4700 UV
Details	Manufacturer Kiilto Oy, - Tampere; Hardener none
Special features	-/-

Result

Classification of thermoplastic wood adhesives for non-structural applications according to EN 204:2016-08



Durability classes: D 4

Average adhesion strength - storage sequence 1 = 13.2 N/mm²

Average adhesion strength - storage sequence 3 = 7.6 N/mm²

Average adhesion strength - storage sequence 5 = 4.3 N/mm²

Basis *)

EN 204:2016-08

*) and corresponding national versions
e.g. DIN EN)

Test report: 17-003553-PR01 PB-K15-09-en-01

Instructions for use

The results obtained can be used as evidence in accordance with the above basis.

Validity

There is no time limit.

When using this document the up-to-dateness of above basis and the conformity of the product have to be observed.

The data and results given relate solely to the tested/described specimen. This test/evaluation does not allow any statement to be made on further characteristics of the present structure regarding performance and quality.

Notes on publication

The ift-Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

ift Rosenheim

31.01.2018



Dr. Ing. Odette Moarcas
Operating Product Officer
Building Material & Semifinished Products



Stefan Hehn, Dipl.-Ing. (FH)
Operating Testing Officer
Material Testing

Identity-Check



www.ift-rosenheim.de/ift-geprueft
ID: EFA-8B488